



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number : **0 425 075 B1**

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification :
29.06.94 Bulletin 94/26

(51) Int. Cl.⁵ : D03D 15/12, D02G 3/44

(21) Application number : 90308053.9

(22) Date of filing : 23.07.90

(54) Fire resistant fabric.

(30) Priority : 27.10.89 US 427738

(43) Date of publication of application :
02.05.91 Bulletin 91/18

(45) Publication of the grant of the patent :
29.06.94 Bulletin 94/26

(84) Designated Contracting States :
AT BE CH DE DK ES FR GB GR IT LI LU NL SE

(56) References cited :
EP-A- 0 323 763
WO-A-87/01140
GB-A- 1 593 048
US-A- 3 729 920
US-A- 4 927 698

(73) Proprietor : SPRINGS INDUSTRIES INC.
Fort Mill South Carolina 29715 (US)

(72) Inventor : Cooke, William Michael
8207 Tradd Court
Charlotte, North Carolina 28210 (US)
Inventor : Hendrix, James Easton
208 Coburn Drive
Spartanburg, North Carolina 29715 (US)
Inventor : Tolbert, Thomas Warren
1823 Apple Tree Lane
Fort Mill, South Carolina 29715 (US)

(74) Representative : MacDougall, Donald
Carmichael et al
Cruikshank & Fairweather
19 Royal Exchange Square
Glasgow G1 3AE, Scotland (GB)

Not : Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 425 075 B1

Description

This invention relates to a protective fabric suitable for use as a heat and flame barrier. More particularly, the fabric may be used as a decorative fire-resistant fabric or used to prevent the combustion of flammable materials by placing the fabric between the heat source and any flammable material.

Various types of protective fabrics have been developed for use in applications in which fabric covered articles (e.g., upholstered articles or office panels) must be capable of withstanding exposure to heat and/or flame without combustion. For example, in upholstered aircraft seating, a heat resistant protective barrier fabric is typically provided between the outer upholstery fabric and the underlying flammable foam cushion to retard or prevent combustion of the cushion in the event of fire. Note, for example, Parker et al U.S. Patent No. 4,463,465 which discloses a barrier fabric which comprises an aramid fabric substrate and an outer aluminum foil layer. The use of an aluminum foil layer, however, has several drawbacks, namely the fabric has limited breathability and the cushioning aspects of the upholstered article are reduced.

Another technique for producing a fire-resistant fabric is to coat the fabric with a fire-resistant compound. Exemplary compounds include those based on an inorganic hydrated compound such as hydrated alumina, hydrated magnesia, magnesium oxychloride, hydrated zinc borate and hydrated calcium borate. Coatings of this type, however, leave spaces between the fibers of the fabric. These spaces or interstices potentially allow hot gases and/or flames to penetrate therethrough and ignite the underlying flammable material.

The introduction of EP-A-0307290 discloses a fire-resistant laminate comprising an underlying flammable layer of, for example, polyurethane foam and a flame barrier formed of a flame durable lining or loose cover.

Intumescent compounds are also used to produce a fire-resistant fabric. For example, Dias US Patent No. 4,216,261 discloses a method of applying an intumescent coating comprising an ammonium phosphate catalyst, a carbonific and a blowing agent. Intumescent coatings, however, require an extra step in the manufacture of the fabric thus the application thereof is time-consuming and expensive.

US-A-3729920 discloses a core yarn suitable for making fabrics for use in making non-inflammable garments having a flame resistant glass core and a sheath of flame resistant fiber such as certain modacrylic fibers.

Summary Of The Invention

The present invention provides a fire-resistant

fabric which is resistant to high temperature fires, it lightweight and breathable and is highly conformable and flexible. The fabric includes a textile fabric substrate formed of corespun yarns, the yarns comprising a core of a flame resistant fibers and a sheath of modacrylic intumescent staple fibers which swell and form a char on exposure to flame. The use of such yarns eliminates the necessity of coating the fabric or of adding a flame barrier metal layer. The fabric may be used either as an exterior fabric or as an underlying barrier fabric in various applications where heat and flame protective properties are required.

Brief Description Of The Drawings

Some of the features and advantages of the invention having been stated, others will appear as the description proceeds, when considered in conjunction with the accompanying drawings in which:

Figure 1 is a greatly enlarged view of a fragment of the corespun yarn of the present invention with a portion of the sheath being removed at one end thereof.

Figure 2 is an enlarged isometric view of a portion of a woven fire-resistant fabric.

Figure 3 is an enlarged isometric view of a portion of a flame resistant laminate which includes a woven fire-resistant laminate which includes a woven fire-resistant fabric as shown in Figure 2, with the layers broken away to more clearly reveal the laminate construction.

Detailed Description Of The Invention

The present invention will be described more fully hereinafter with reference to the accompanying drawings, in which preferred embodiments of the invention are shown. This invention can, however, be embodied in many different forms and should not be construed as limited to the embodiment set forth herein.

Referring to Figure 1, the fabrics of the present invention are formed from corespun yarns 10 comprising a core 11 of fire-resistant fibers and sheath 12 of modacrylic intumescent fibers. Exemplary fire-resistant core fibers may include fibers of glass, polybenzimidazoles, polyimides, various metals, quartz, ceramics, polyetherketones, polyetheretherketones, polyetherketoneketones, polyetheretherketoneketones, polyetherimides, polysulfones, polyarylates, polyaryletherketones, polyamide-imides, polyarylsulfonates, polythrsulfones, polyketones, polyphenyl sulfides, polyaramids such as Kevlar® or Nomex®, and carbon and carbonizable compounds and blends thereof. Additionally, the core fibers may be formed from corespun yarns and may include fire-resistant staple fibers as the sheath. These core fibers typically have a diameter of from about 5 to 6 μ m.

The modacrylic intumescent staple fibers have a diameter of about 1.3 denier and are characterized by being a long chain synthetic polymer containing 35-85% acrylonitrile units. An exemplary modacrylic intumescent fiber is SEF® fiber manufactured by Monsanto Corporation of St. Louis, Missouri. Additionally, the modacrylic fibers may be blended or commingled with small amounts of fibers which form a char on exposure to flame such as wool, silk and cellulose while maintaining the intumescent properties of the modacrylic fibers.

The yarns of these fabrics are of co-spun construction and are formed by suitable apparatus such as ring spinning, DREF® spinning or preferably using a Murata air jet spinning apparatus. Air jet spun yarn, the production of which is described for example in co-pending, European Patent Application No. 89309168.6 filed on 8th September, 1989, is characterized by having the majority of its fibers extending parallel to the yarn axis, with the ends of some of the modacrylic fibers intermittently extending out of the fiber bundle and wrapped or twisted around the other fibers to bind the whole together. Ring spun yarn is generally characterized by having its fibers arranged substantially uniformly in a helical arrangement, and the fibers are held in this arrangement by the twist of the yarn. If DREF® spinning is utilized, such as described in Fehrer U.S. Patent Nos. 4,249,368 and 4,327,545, the core may be of multi-fiber construction with minor amounts of fibers which improve the mechanical characteristics of the yarn such as nylon, PET, cotton and cellulose while not adversely affecting the flame durability of the majority of fire-resistant fibers described above.

The co-spun yarns may be formed into a textile fabric substrate using any of the various fabric constructions, such as fabrics of woven, non-woven, knitted including warp and circular knits, braided, warp lay and scrim reinforced web construction. Referring to Figure 2, a particular textile fabric substrate having a woven construction is illustrated. The woven textile fabric substrate 20 is formed by warp yarns 21 interengaged with weft yarns 23 at spaced intervals and is woven by conventional techniques. Such a woven fabric typically comprises 20/1 to 10/1 cotton count yarns for pillow and mattress ticking and 1/1 to 10/1 cotton count yarns for decorative upholstery.

In general, the fire-resistant fabric is useful both as a flame barrier and as a decorative fabric. In everyday use, the fabrics of the present invention are lightweight and flexible because of the absence of a metal foil layer or a coating layer, and thus can easily be conformed to the shape of the article. Additionally, the fabrics are breathable because of their porosity. The porosity and breathability of a fabric is expressed in terms of the "air permeability" of the fabric. Air permeability is measured in accordance with ASTM Standard Test Method D737 for Air Permeability of

Textile Fabrics. The rate of flow through a known area of fabric is adjusted to secure a prescribed pressure differential between the two surfaces of the fabric in the test area and from this rate of flow the air permeability of fabric is determined. Thus, using a 4 mm calibration orifice to which air is blown at a rate of about 3.6 cubic feet per minute, the woven fabric of the present invention has an air permeability of about 10 to 300 cubic feet per minute.

In particular, the air permeability of the barrier fabric assures good air circulation for comfort. The air permeability of the barrier fabric is also particularly important when the barrier is used with cushioned upholstered articles used for seating. Because of the air permeability of the flame barrier fabric, air is free to escape from the cushion when it is compressed. Thus, the fabric avoids the hard and uncomfortable "balloon" effect that is characteristic of most prior art air impermeable flame barrier fabrics.

However, on exposure to flame, the modacrylic intumescent fibers of the fabric swell and char. As a result of the swelling, the pores or interstices between the yarns are closed. The char is substantially incombustible and has cellular characteristics. The char thus acts as a flame barrier and limits the penetration of flames and hot gases through the fabric to ignite the underlying flammable material. The core fibers of the co-spun yarns also contribute to the flame resistant properties of the fabric in that they remain intact on exposure to a flame and provide a lattice or support for the modacrylic intumescent sheath fibers. Additionally, if a co-spun fiber is used, the core itself may provide flame barrier properties.

Barrier fabrics of the present invention are particularly suitable as flame barriers for upholstered articles since the flame barrier fabric can easily be conformed to the shape of the article. For example, as shown in Figure 3, it is particularly effective as a barrier in an upholstered article wherein the fabric 20 is placed between a underlying flammable layer 30 such as polyurethane foam and an upholstery layer 40 preferably using an adhesive layer 45 such as a latex anti-slide adhesive. Additionally, the fabrics may be used as flame resistant textile articles such as mattress and pillow ticking, mattress and pillow covers, draperies, zipper tape, tents, awnings, field fire shelters, sleeping bag covers, marine covers, tarpaulins, protective apparel and the like.

Claims

1. A fire-resistant laminate comprising an underlying flammable layer (30), a flame barrier fabric (20) overlying said underlying flammable layer (30), characterized in that said flame barrier fabric (20) comprises an air permeable flame durable textile fabric substrate formed of co-spun

yarns (10), said yarns (10) comprising a core (11) of a flame resistant fiber and a sheath (12) of modacrylic intumescent staple fibers which swell and form a char on exposure to flame, the swelling closing the pores or interstices between the yarns and the char thus acting as a flame barrier to limit the penetration of hot gases and flames through the fabric to ignite the underlying fabric layer, the core fibers providing a lattice or support for the char.

2. A fire-resistant laminate according to claim 1 wherein the textile fabric substrate is of woven, non-woven, knitted, braided, warp lay and scrim reinforced web construction.

3. A fire-resistant laminate according to claim 1 wherein the flame resistant fiber of the core (11) is selected from the group consisting of glass, polybenzimidazole, polyimides, various metals quartz, ceramics, polyetherketones, polyetheretherketones, polyetherketonesketones, polyetheretherketonesketones, polyetherimides, polysulfones, polyarylates, polyaryletherketones, polyamideimides, polyarylsulfones, polyethersulfones, polyketones, polyphenylene sulfides, polyaramids and carbon and carbonizable compounds and blends thereof.

4. A fire-resistant laminate according to claim 3 wherein the flame resistant fiber of the core (11) is a corespun fiber.

5. A fire-resistant laminate according to claim 1 wherein the modacrylic intumescent staple fibers are blended with a fiber selected from the group consisting of wool, silk and cellulosic fibers.

6. A fire-resistant laminate according to claim 1 wherein the underlying flammable layer (30) comprises a polyurethane foam.

Patentansprüche

1. Schwer entflammbares Laminat mit einer entflammbaren Unterschicht (30) und mit einem Flammenschutzgewebe (20) auf der entflammbaren Unterschicht (30), dadurch gekennzeichnet, daß das Flammenschutzgewebe (20) eine luftdurchlässige, feuerbeständige textile Gewebeträgerschicht aus Kernmantelfäden (10) aufweist, daß die Kernmantelfäden (10) aus einem Kern (11) aus einer schwer entflammbaren Faser und aus einem Mantel (12) aus sich aufblähenden Modakryl-Stapelfasern bestehen, die unter Hitzeeinwirkung anschwellen und eine künstliche

Verkohlungsschicht bilden, wobei das Anschwellen die Poren oder Zwischenräume zwischen den Fäden schließt und die künstliche Verkohlungsschicht somit als Flammenbarriere wirkt, um das Durchdringen von heißen Gasen und Flammen, welche die untere Gewebeschicht entzünden, durch das Gewebe zu begrenzen, und daß die Kernfäden eine Gitter- oder Tragstruktur für die künstliche Verkohlungsschicht bilden.

2. Schwer entflammbares Laminat nach Anspruch 1, bei dem die textile Gewebeträgerschicht aus einer gewobenen, nicht-gewobenen, gestrickten, geflochtenen Kettenlagen- und Gewebeverstärkungsstruktur besteht.

3. Schwer entflammbares Laminat nach Anspruch 1, bei dem die schwer entflammbare Faser des Kerns (11) aus jener Stoffgruppe ausgewählt ist, welche Glas, Polybenzimidazol, Polyimid, verschiedene Quarzmetalle, keramische Werkstoffe, Polyetherketon, Polyetheretherketon, Polyetherketonketon, Polyetheretherketonketon, Polyetherimid, Polyethersulfon, Polyarylat, Polyaryletherketon, Polyamid-Imid, Polyarylsulfon, Polyethersulfon, Polyketon, Polyphenylen-Sulfid, polyaramid und Karbon und karbonisierbare Komponenten und Mischungen davon enthält.

4. Schwer entflammbares Laminat nach Anspruch 3, bei dem die schwer entflammbare Faser des Kerns (11) eine Kernmantelfaser ist.

5. Schwer entflammbares Laminat nach Anspruch 1, bei dem die sich aufblähenden Modakryl-Stapelfasern mit einer Faser aus der Wolle, Seide und Cellulosefasern enthaltenden Gruppe gemischt ist.

6. Schwer entflammbares Laminat nach Anspruch 1, bei dem die entflammbare Unterschicht (30) einen Polyurethanschaum enthält.

Revendications

1. Lamifié résistant au feu comprenant une couche sous-jacente inflammable (30), un tissu arrête-flammes (20) situé au-dessus de ladite couche sous-jacente inflammable (30), caractérisé en ce que ledit tissu arrête-flammes (20) comprend un substrat en textile résistant à la flamme et perméable à l'air, formé de filés à fil d'âme (10), lesdits filés (10) comprenant une âme (11) en une fibre résistante à la flamme et un guipage (12) en fibres discontinues modacryliques intumescents qui gonflent et forment un produit de carboni-

sation lors de l'exposition à la flamme, le gonflement fermant les pores ou interstices entre les filés et le produit de carbonisation agissant ainsi comme un arrête-flammes pour limiter la pénétration de gaz chauds et de flammes à travers le tissu pour enflammer la couche en tissu sous-jacente, les fibres de l'âme constituant un réseau ou support pour le produit de carbonisation.

5

2. Lamifié résistant au feu selon la revendication 1, dans lequel le substrat en textile a une structure de tissu renforcée tissée, non tissée, tricotée, tressée, à commettage de la chaîne et en canevass.

10

15

3. Lamifié résistant au feu selon la revendication 1, dans lequel la fibre résistante à la flamme de l'âme (11) est choisie parmi le groupe constitué du verre, du polybenzimidazole, des polyimides, du quartz de divers métaux, des céramiques, des polyéthercétones, des polyétheréthercétones, des polyéthercétonescétones, des polyétheréthercétonescétones, des polyétherimides, des polysulfones, des polyarylates, des polyaryléthercétones, des polyamide-imides, des polyarylsulfones, des polyéthersulfones, des polycétones, des sulfures de polyphénylène, des polyaramides et des composés de carbone et carbonisables, et des mélanges de ceux-ci.

20

25

30

4. Lamifié résistant au feu selon la revendication 3, dans lequel la fibre résistante à la flamme de l'âme (11) est une fibre à fil d'âme.

5. Lamifié résistant au feu selon la revendication 1, dans lequel les fibres discontinues modacryliques intumescents sont mélangées avec une fibre choisie parmi le groupe constitué de la laine, de la soie, et des fibres cellulosiques.

35

40

6. Lamifié résistant au feu selon la revendication 1, dans lequel la couche sous-jacente inflammable (30) comprend une mousse de polyuréthane.

45

50

55






FIG. 3.